Novasil[®] M 375

The 1-component all-round adhesive for industrial purposes

M 375

Characteristics

- > 1-component adhesive based on hybrid polymer STP
- Also on damp substrates
- Broad adhesion spectrum
- Strong initial adhesion
- High final strength
- Elastic
- Good plastic bonding
- Fast thorough hardening
- Silicone-free
- Free of isocyanates
- Compatible with coatings according to DIN 52452
- Can be painted and varnished please observe application instruction in TDS

Fields of application

Lighting and electronics industry:

- Elastic bonding and sealing of lamp casings
- Heating, ventilation and plant construction:
- > Sealing of connecting and expansion joints for air-conditioning and ventilation technology purposes
- **General Industry:**
- > Elastic bonding of same and different materials such as stainless steel, aluminium and some types of plastic
- Elastic bonding for bodywork and vehicle construction purposes, wagon and container construction, metalwork and apparatus construction

۶

Technical properties

~ 10
~ 3
+ 5 / + 40
pasty, stable
~ 1,5
~ 60
~ 2,4
~ 150
~ 2,7
- 40 / + 100 1
12 ²

1) temporarily (90 minutes) up to + 150 °C

2) from production

Hermann Otto GmbH

Krankenhausstr. 14 | 83413 Fridolfing, Germany & +49 8684 908-0 | @ info@otto-chemie.de www.otto-chemie.com Application advice
+49 8684 908-4300
tae@otto-chemie.de



These data are not suitable for the issue of specifications. Please contact OTTO-CHEMIE before issuing specifications.

Pretreatment

The adherent surfaces have to be clean, free from dust and grease as well as sustainable.

The adhesive surfaces must be cleaned and any contamination such as release agents, preservatives, grease, oil, dust, water, old adhesives/sealants and other substances impairing adhesion must be removed.

The demands on elastic sealings and bondings depend on the respective exterior influences. Extreme fluctuations in temperature, tensile or shear forces, repeated contact with water etc. demand high requirements of a bonding. In such cases it is advisable to apply primer in order to achieve a resilient bonding. Please consult our technical department.

Important information

Before applying this product the user has to ensure that the materials in the area of contact (solid, liquid and gaseous) are compatible with it and also amongst each other and do not damage or alter (e. g. discolour) each other. As for the materials that will be used at a later stage in the surrounding area of the product the user has to clarify beforehand that the substances of content or evaporations do not lead to an impairment or alteration (e. g. discolouration) of the product. In case of doubt the user should consult the respective manufacturer of the material.

Paints, lacquers, plastics and any other coatings must be compatible to the adhesive/sealant.

For UV-loaded bonds/seals of glass, we recommend the use of a high-quality silicone adhesive/sealant.

Not suitable for sealing / bonding copper upon impact of UV-radiation and temperature.

For UV-loaded bonds/seals of transparent plastics such as acrylic glass we recommend the use of a high-quality silicone adhesive/sealant.

The colours of the sealant may be affected by environmental influences (high temperature, chemicals, vapours, UV-radiation). This does not affect the characteristics of the product.

Application information

In order to achieve optimal adhesion and good mechanical characteristics, the entrapment of air in the joint must be avoided. Curing time can be reduced by humidification and increased temperatures.

For the full-surface bonding of steam-tight substrates the adhesive should be moistened.

Our product can be overcoated with paint or varnish. The compatibility between the coating and our product has to be checked before the application by the user/processor - possibly under production conditions. Our OTTO application technology will gladly support you non-committally. If, in exceptional cases, after succesful compatibility test our product is coated over the entire surface, this coating must also be able to follow the elastic movement of the sealant. Otherwise crack formations in the coat of paint or optical impairments may occur.

Due to the many possible influences during and after application, the customer always has to carry out trials first. STORAGE:

Please observe the recommended shelf life which is printed on the packaging.

We recommend to store our products in unopened original packagings dry (< 60 % RH) at temperatures of +15 °C up to +25 °C. If the products are stored and / or transported at higher temperatures / air humidity for longer periods (some weeks), a diminuition of durability or a change of material characteristics may arise.

If stored for a longer period at higher temperatures (≥ 30 °C) a diminishment of the initial adhesion may occur.

Packaging

	310 ml cartridge
black	M375-04-C04
Pieces per packaging unit	20
Pieces per pallet	1200

Further delivery forms available on request

Due to typographical reasons the colours shown below may differ from the original colours of the products.

Safety precautions

Please observe the material safety data sheet.

Disposal

Information about disposal: Please refer to the material safety data sheet.

Warranty information

The above information and our technical application advice, whether verbal, in writing or by means of tests, are provided to the best of our knowledge, but are non-binding, including with regard to any third-party property rights. The information in this publication does not exempt the processor from carrying out their own tests on our products with regard to their suitability for

the intended processes and purposes. The application, use and processing of our products and the products manufactured on the basis of our technical application advice are beyond our control and are therefore the sole responsibility of the processor. If the application for which our products are used is subject to an official authorisation requirement, the user is responsible for obtaining these authorisations. We reserve the right to adapt the product to technical progress and new developments. For the rest, we refer to our General Terms and Conditions, in particular with regard to any liability for defects. You can find our GTC at www.otto-chemie.de.