



# Confirmation

Eurofins Product Testing A/S confirms that a sample of a Silicone Sealant with the name

**OTTOSEAL<sup>®</sup> S 120**  
supplied by  
**Hermann Otto GmbH**

showed low VOC contents in a test as specified in LEED credit EQ 4.1 (adhesives and sealants).

VOC contents were below the limit value specified as 420 grams VOC minus water per liters for silicone sealants.

The test has been performed in October 2010, see test report no. G04825\_03.

Volatiles content was calculated by Eurofins.  
Water content was specified by manufacturer.  
Solids content was determined by Eurofins.

**With this confirmation, use of the product may qualify for fulfillment of LEED credit EQ 4.1 (adhesives and sealants).**

---

17 November 2015

Lise L. Clement  
Chemist

Janne R. Norup  
Chemist

Eurofins Product Testing A/S  
Smedeskovvej 38  
DK 8464 Galten / Denmark

Tel +45 70 22 42 76  
Fax +45 70 22 42 75

[www.product-testing.eurofins.com](http://www.product-testing.eurofins.com)



Hermann Otto GmbH  
 Alois Parzinger  
 Krankenhausstr. 14  
 83413 Fridolfing  
 Germany

**Eurofins Product Testing A/S**  
 Smedeskovvej 38  
 DK-8464 Galten  
 Denmark

Tel. +45 70 22 42 76  
 Fax +45 70 22 42 75  
 eurofins@eurofins.dk  
 www.eurofins.com/product-emissions

Date  
 17 November 2015

Your ref.  
 -

Our ref.  
 G04825\_03

## Test Report – LEED EQ 4.1 - 2009

### Sample material

Sample identification	OTTOSEAL® S 120
Product type	Silicone Sealant
Product data, according to manufacturer	Density: 1.02 g/ml at 20 °C
Date received	1 October 2010
Analytical period	October 2010

### Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty
LEED EQ 4.1-2009 ASTM D 2369 - 04	Gravimetric	Volatile/Solid Content of Coatings	1 g/l	0.1 %
Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of triple testing. The result was calculated as: $([g \text{ all volatiles}] - [g \text{ water}] - [g \text{ exempt compounds}]) / ([l \text{ material}] - [l \text{ water}] - [l \text{ exempt compounds}])$				

### Analytical results

	Solid content, % mass	Water content, % mass	VOC less water less exempt compounds, g/l	VOC limit g/l
<b>OTTOSEAL® S 120</b>	94.4 %	0 **	57	420 *

\* VOC limit for Silicone Sealants (other Sealants).

\*\* Given by the client.

Eurofins Product Testing A/S

Lise L. Clement  
 Chemist

Janne R. Norup  
 Chemist