

Chemical resistance

OTTOSEAL[®] M 380

OTTOSEAL [®] M 380	
Chemicals	Assessment
Isopropyl	temporarily resistant
Ethylalcohol	not resistant
Caustic soda solution 10%	resistant
Ammonia 10%	resistant
Ammonia 25%	resistant
Acetic acid 10 %	resistant
Hydrochloric acid 10%	temporarily resistant
Sulphuric acid 10 %	resistant
Hydrogen peroxide 10 %	resistant
Sodium hypochlorite 2 %	resistant
Petroleum ether / mineral oil	temporarily resistant

Short-term resistance refers to a maximum application time of 72 hours.
The tests were carried out at room temperature.

[Please note technical data sheet!](#)