



# Confirmation

Eurofins Product Testing A/S confirms that a sample of a Polyurethane Adhesive with the name

## **OTTOCOLL® P 520 2-Components**

supplied by

## **Hermann Otto GmbH**

showed low VOC contents in a test specified in LEED 2009 credit EQ c4.1 (adhesives and sealants).

VOC contents were below the limit value specified as 70 grams VOC minus water per liters for "Multipurpose Construction Adhesives".

The test has been performed in October 2011, see test report no. G10525.

Volatiles content was calculated by Eurofins.  
Water content was set to zero.  
Content of exempt compounds was set to zero.  
Solids content was determined by Eurofins.

**With this confirmation, use of product OTTOCOLL® P 520 2-Components may qualify for fulfilment of LEED 2009 credit EQ c4.1 (adhesives and sealants).**

---

26 October 2011

---

Inge Bondgaard  
Chemical engineer, head of customer centre

Eurofins Product Testing A/S  
Smedeskovvej 38  
DK 8464 Galten / Denmark

Tel +45 70 22 42 76  
Fax +45 70 22 42 75

[www.product-testing.eurofins.com](http://www.product-testing.eurofins.com)



Hermann Otto GmbH  
 Alois Parzinger  
 Krankenhausstr. 14  
 83413 Fridolfing  
 Germany

Eurofins Product Testing A/S  
 Smedeskovvej 38  
 DK-8464 Galten  
 Denmark

Tel. +45 70 22 42 76  
 Fax +45 70 22 42 75  
 voc@eurofins.dk  
 www.eurofins.com/product-emissions

Date  
 11 October 2011

Your ref.  
 -

Our ref.  
 G10525/IB

## Test Report – LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

### Sample material

Sample identification	<b>OTTOCOLL® P 520 2-Components</b>
Product type	Polyurethane Adhesive
Product data, according to manufacturer	Density: 1.48 g/ml at 20 °C ** Water content: 0 g/l** Exempt compounds***.
Date received	7 September 2011
Analytical period	October 2011

### Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty
LEED 2009 EQ c4.1 ASTM D 2369 - 10	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 %

Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The result was calculated as:

$$([g \text{ all volatiles}] - [g \text{ water}] - [g \text{ exempt compounds}]) / ([l \text{ material}] - [l \text{ water}] - [l \text{ exempt compounds}])$$

U<sub>m</sub> (%): The expanded uncertainty U<sub>m</sub> is equal to 2 x RSD%, see also [www.eurofins.dk](http://www.eurofins.dk), keyword: Måleusikkerhed

### Analytical results

	Solid content, % mass	Water content, % mass	Exempt compounds, % mass	VOC less water less exempt compounds, g/l	VOC limit g/l
<b>OTTOCOLL® P 520 2-Components</b>	97	0**	0***	38	70*

\* VOC limit for "Multipurpose Construction Adhesives"

\*\* Given by the client

\*\*\* Not information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

Inge Bondgaard  
 Chemical engineer, Head of customer centre