



Confirmation

Eurofins Product Testing A/S confirms that a sample of a PU Adhesive with the name

OTTOCOLL P 85
supplied by
Hermann Otto GmbH

showed low VOC contents in a test as specified in LEED credit EQ 4.1 (adhesives and sealants).

VOC contents were below the limit value specified as 70 grams VOC minus water per liters for Multipurpose Construction Adhesives.

The test has been performed in October 2010, see test report no. G04831.

Volatiles content was calculated by Eurofins.
Water content was specified by manufacturer.
Solids content was determined by Eurofins.

With this confirmation, use of product OTTOCOLL P 85 may qualify for fulfilment of LEED credit EQ 4.1 (adhesives and sealants).

29 October 2010

Inge Bondgaard
Chemical engineer

Eurofins Product Testing A/S
Smedeskovvej 38
DK 8464 Galten / Denmark

Tel +45 70 22 42 76
Fax +45 70 22 42 75

www.product-testing.eurofins.com



Hermann Otto GmbH
 Alois Parzinger
 Krankenhausstr. 14
 83413 Fridolfing
 Germany

Eurofins Product Testing A/S
 Smedeskovvej 38
 DK-8464 Galten
 Denmark

Tel. +45 70 22 42 76
 Fax +45 70 22 42 75
 eurofins@eurofins.dk
 www.eurofins.com/product-emissions

Date
 19 October 2010

Your ref.

-

Our ref.
 G04831/IB

Test Report – LEED EQ 4.1 - 2009

Sample material

Sample identification	OTTOCOLL P 85
Product type	PU Adhesive
Product data, according to manufacturer	Density: 1.46 g/ml at 20 °C
Date received	1 October 2010
Analytical period	October 2010

Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty
LEED EQ 4.1-2009 ASTM D 2369 - 04	Gravimetric	Volatile/Solid Content of Coatings	1 g/l	0.1 %
Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of triple testing. The result was calculated as: ([g all volatiles] - [g water] - [g exempt compounds]) / ([l material] - [l water] - [l exempt compounds])				

Analytical results

	Solid content, % mass	Water content, % mass	VOC less water less exempt com- pounds, g/l	VOC limit g/l
OTTOCOLL P 85	95.4 %	0 **	67	70 *

* VOC limit for Multipurpose Construction Adhesives.

** Given by the client.

Eurofins Product Testing A/S

Inge Bondgaard
 Chemical engineer