

# OTTOCORD

## PE-B2

### Technical Datasheet

**Characteristics:**

- Extruded backfilling material made of polyethylene (PE)
- **For application in interior and exterior areas**
- Closed-cell according to DIN 18540
- Water-repellent
- Normally flammable

**Fields of application:**

- Backfilling of joints in interior and exterior areas
- For building construction joints according to DIN 18540

**Standards and tests:**

- Tested fire behaviour: normal inflammable building material (class E according to DIN EN 13501-1)

**Technical properties:**

Density in raw state [kg/m <sup>3</sup> ]	20 - 35
Tensile strength [kPa]	200 - 300
Temperature resistance from/to [°C]	- 40 / + 60
Colour	grey

These data are not suitable for the issue of specifications. Please contact OTTO-CHEMIE before issuing specifications.

**Application information:**

The optimum ratio of joint width to joint depth is an important requirement for as long a life as possible of an elastic joint. Building component joints are frequently too deep for a professional joint dimensioning. For this reason, a limit of the joint depth must be performed using the closed-cell OTTOCORD PE-B2 back-up foam rod, simultaneously preventing a three-edge bond in order to restrict the flexibility of the sealant in the joint. The closed-cell back-up foam rod is pressure-resistant and non-water absorbent, making it suitable for both insider and outside. Press OTTOCORD PE-B2 into the joint using a blunt tool. Do not use sharp objects, otherwise the closed-cell surface could become damaged. The diameter of the back-up foam rod should be around 20% greater than the width of the joint so that it can be applied to the joint applying pressure and so that it then retains an oval shape in the joint. Further information is available from the OTTO Professional guide "Joints perfectly formed".

Packaging:

Diameter	PE bag with Euro perforation in m	Order Code
6mm	5	PE-6-5
8mm	5	PE-8-5
10mm	5	PE-10-5
13mm	5	PE-13-5
15mm	5	PE-15-5

  

Diameter	Single box in m	Order Code
6mm	100	PE-6-100
8mm	100	PE-8-100
10mm	100	PE-10-100
13mm	100	PE-13-100
15mm	100	PE-15-100
20mm	50	PE-20-50
25mm	50	PE-25-50
30mm	25	PE-30-25
40mm	135*	PE-40-135
50mm	90*	PE-50-90

Please order per box! \*Pieces per meter

Disposal:

Product residues can be disposed of along with industrial waste as mixed plastics. Packaging materials (cardboard boxes, foils) are recyclable and hence should be recycled.

Warranty information:

All information in this publication is based on our current technical knowledge and experience. However, since conditions and methods of use and application of our products are beyond our control, we suggest that you test the product before final use. Information given in this technical data sheet and explanations of OTTO-CHEMIE in connection with this technical data sheet (e.g. service description, reference to DIN regulations etc.) is not to be seen as a warranty. Warranties require a separate written declaration of OTTO-CHEMIE to prove their validity. The characteristics stated in this data sheet define the characteristics of the article broadly and concludingly. Suggestions of use are not to be taken as confirmation of the appropriateness for the recommended intended use. We reserve the right to alter the product, adjusting it according to technical progress and new developments. We are at your disposal both for inquiries as well as specific application problems. If a governmental approval or clearance is necessary for the application of our products, the user is responsible for the obtainment of such. Our recommendations do not excuse the user from the obligation to take into consideration the possibility of infringement of third parties' rights and - if necessary - resolving it. For the rest our general terms and conditions apply, in particular regarding a possible liability for defects. You can find our general terms and conditions on our homepage: <http://www.otto-chemie.de/en/terms-and-conditions>